

# **METHOD OF APPLYING A THERMALLY SETTABLE COATING TO A PATTERNED SUBSTRATE**

## 5 **Related Application**

[0001] This application claims priority on pending international application No. PCT/CA02/01864 filed 3 December 2002 which is incorporated herein by reference.

10

## **Technical Field**

[0002] This application relates to a method of applying a thermally settable coating to a patterned substrate, such as an imprinted asphalt surface. The coating may be applying by placing one or more pre-formed thermoplastic sheets on the substrate and heating the sheets *in situ* to conform to the thermoplastic material to the underlying pattern.

15

## **Background**

20

[0003] Various methods for forming patterns in asphalt surfaces and other substrates are known in the prior art. The Applicant is the owner of United States Letters Patent No. 5,215,402 which describes a method of forming a pattern in an asphalt surface using a removable template. The template is compressed into a pliable asphalt surface to imprint a predetermined pattern simulating, for example, the appearance of bricks, cobblestones, interlocking paving stones or the like. The template is then lifted clear of the asphalt surface and the asphalt is allowed to harden.

25

30

[0004] In one embodiment of the '402 invention a thin layer of a cementitious coating may be applied to the imprinted asphalt to enhance the brick and mortar or other desired visual effect. The decorative coating may be applied, for example, by applying concrete powder and a colorant in the form of a slurry which is spread throughout the asphalt

35

surface and allowed to harden. This is a relatively time consuming and labour-intensive process. Various other acrylic, epoxy or latex-based protective coatings may similarly be applied to the imprinted surface after the impression step to seal the surface and enhance its visual appeal.

[0005] One drawback to the '402 method is that the decorative coating may wear off over time, particularly in high traffic areas. Further, as mentioned above, application of coatings in a liquid form is time consuming and poses technical difficulties. For example, if the coating is not spread to a consistent depth an unappealing visual effect may result. The need has therefore arisen for improved methods for coating asphalt surfaces by application of heat to pre-formed thermo-plastic sheets.

[0006] It is known in the prior art to impress patterns in thermoplastic coatings on-site for functional or decorative purposes. For example, Prismo Universal Corporation has used and described a process for applying a relative thick layer (i.e. approximately 15 mm) of thermoplastic to an underlying substrate in a heated, pliable form. The thermoplastic is then manually stamped in the desired pattern by applicators wearing insulated, heat-protective clothing. The process is very labour-intensive and potentially dangerous. Since the stamping is performed manually, it is difficult to apply consistently render complicated patterns over large surface areas. Moreover, the stamping is intended to impress patterns in the thick thermoplastic layer rather than the underlying substrate.

[0007] The need has therefore arisen for improved methods and materials for applying a thermally settable coating to a patterned substrate, such as an imprinted asphalt surface.

### Summary of Invention

5 [0008] In accordance with the invention, a method of applying a coating to a substrate is provided comprising (a) forming a first pattern in the substrate; (b) placing a pre-formed thermally settable sheet on the substrate; and (c) heating the sheet *in situ* to a temperature sufficient for the sheet to adhere to the substrate in a configuration conforming to the first pattern.

10

[0009] Preferably the sheet is formed of a thermoplastic material and the substrate is an asphalt surface. The sheet may include a first surface in contact with the asphalt surface and a second surface not in contact with the asphalt surface. The sheet preferably has a thin profile so that the thermoplastic is coated on the asphalt surface in a thickness between 30 - 150 mil., or more preferably between 50 - 125 mil.

15

[0010] The first pattern may be formed in the asphalt surface when it is in a pliable state. For example, the first pattern may be formed in a recently formed asphalt surface comprising hot asphalt or in a pre-existing, re-heated asphalt surface. In one embodiment the first pattern is formed by placing a template on the asphalt surface while it is in a pliable state; imprinting the template into the asphalt surface to form the first pattern; and removing the template from the asphalt surface to expose the pattern.

25

[0011] The step of heating the sheet *in situ* may comprise gradually increasing the temperature of the sheet by providing a heating apparatus having a support frame extending over the sheet, the apparatus having at least one heater which is mounted for movement on the support frame in a travel path which periodically passes over the sheet. The sheet may be

30

heated to a temperature between approximately 150 - 450 °F, or more preferably 300 - 400 °F.

5       **[0012]**       The sheet may be subdividable into a plurality of discrete sections. Additionally or alternatively, a plurality of separate sheets may be provided which may be aligned adjacent one another to cover the asphalt surface. The size, shape, color and texture of the sheets may be selected for functional and/or decorative purposes. For example, each sheet may be formed in a second pattern which matches the first pattern  
10       formed in the asphalt surface.

15       **[0013]**       In an alternative embodiment of the invention the first pattern may be formed in the thermoplastic sheet and the substrate simultaneously. In this embodiment the pre-formed thermally settable sheet is placed on an unpatterned substrate. The sheet is then gradually heated *in situ* to a temperature sufficient for the first surface of the sheet to adhere to the substrate. The sheet and the substrate are then imprinted to form the first pattern, such as by compressing a template placed on the second, exposed surface of the sheet. Prior to placing the template on the sheet second  
20       surface, the second surface may be treated with a bond reduction agent or coolant to minimize adherence between the template and the hot thermoplastic material of the pre-formed sheet.

#### Brief Description of Drawings

25

**[0014]**       In drawings which illustrate embodiments of the invention, but which should not be construed as restricting the spirit or scope of the invention in any way,

30

**[0015]**       Figure 1 is an perspective view of a template for forming a pattern in a pliable asphalt surface.

[0016] Figure 2 is a diagrammatic side view of the template of Figure 1 being compressed into an asphalt surface with a drum roller.

5 [0017] Figure 3 is a perspective view of an apparatus comprising reciprocating infrared heaters for gradually heating a work site.

[0018] Figure 4 is an exploded, perspective view of a pre-formed thermoplastic sheet being placed on a patterned asphalt surface.

10

[0019] Figure 5 is a perspective view showing the heaters of the apparatus of Figure 3 passing over the pre-formed sheet of Figure 4.

15 [0020] Figure 6 is a perspective view showing the thermoplastic material of the sheet of Figures 4 and 5 melted on the patterned asphalt surface to form a coating thereon.

[0021] Figure 7 is a cross-sectional view showing the coating conforming to the contour of the patterned asphalt surface.

20

[0022] Figure 8 is a an exploded, perspective view of a pair of pre-formed thermoplastic sheets being placed in alignment on a patterned asphalt surface.

25 [0023] Figure 9 is a perspective view showing the heaters of the apparatus of Figure 3 passing over the pre-formed sheets of Figure 8.

30 [0024] Figure 10 is a perspective view of an alternative embodiment of the invention comprising placement of a pre-formed thermoplastic sheet on an unpatterned asphalt surface and bonding of the sheet to the surface using the heaters of Figure 3.

[0025] Figure 11 diagrammatically illustrates the step of applying a bond reduction agent or a coolant to the exposed surface of the thermoplastic sheet.

5

[0026] Figure 12 is a perspective view illustrating the step of simultaneously forming a pattern in the thermoplastic coating and underlying asphalt surface using a removable template.

10 Description

[0027] Throughout the following description, specific details are set forth in order to provide a more thorough understanding of the invention. However, the invention may be practiced without these particulars. In  
15 other instances, well known elements have not been shown or described in detail to avoid unnecessarily obscuring the invention. Accordingly, the specification and drawings are to be regarded in an illustrative, rather than a restrictive, sense.

20 [0028] This application relates to a method of applying a thermally settable coating 10 to a patterned substrate, such as an asphalt surface 12. As shown in Figures 4 - 6, coating 10 may be initially applied to asphalt surface 12 in the form of one or more pre-formed sheets 14. Sheets 14 are then gradually heated *in situ* as described below until a consistent bond is  
25 achieved between sheets 14 and asphalt surface 12, thereby forming coating 10. The heating process causes sheets 14 to conform to a pattern formed 22 in the underlying surface 12 to thereby enhance its decorative or functional effect (Figures 6 and 7).

30 [0029] As used in this patent application the term heating "*in situ*" refers to heating pre-formed sheets 14 at the installation site rather than

applying hot thermoplastic in a liquid form in a conventional manner directly to asphalt surface 12 and allowing it to harden. As used in this patent application "asphalt" means a paving compound for constructing roads, driveways, walkways and the like which consists of a combination of bituminous binder, such as tar, and an aggregate, such as sand or gravel. As will be appreciated by a person skilled in the art, applicant's method could also be applied to other types of patterned substrates, such as concrete or other materials capable of receiving and adhering to settable coating 10.

10

[0030] As shown best in Figure 4, each pre-formed sheet 14 has a first surface 16 which is placed in contact with asphalt surface 12 and a second, exposed surface 18 which is not placed in contact with asphalt surface 12. In one embodiment of the invention the thickness of each sheet 14 between surfaces 16, 18 is within the range of approximately 30 - 150 mil in thickness, or more particularly 50 - 125 mil in thickness. Sheets 14 may be formed from thermoplastic material and are available from various suppliers, such as Lafarge Road Markings, Flint Trading, Inc. and Avery Dennison Corporation. Sheets 14 may be selected for functional purposes, such as traffic markings or corporate logos, or may be purely decorative. As shown in Figure 8, a plurality of sheets 14 may be juxtaposed together in a non-overlapping arrangement to completely cover asphalt surface 12. In an alternative embodiment, edge portions of adjacent sheets 14 could be partially overlapping. In another alternative embodiment sheets 14 may be arranged to only partially cover asphalt surface 12, such as by maintaining gaps between adjacent sheets 14. Further, each sheet 14 may either be continuous or discontinuous. For example, each sheet 14 could include openings or slots formed therein. As will be apparent to a person skilled in the art, the shape and configuration of sheets 14 may vary without departing from the invention.

[0031] A pattern may be formed in asphalt surface 12, for example, according to the method of the Applicant described in United States Letters Patent No. 5,215,402 which is hereby incorporated by reference. More particularly, a template 20 is placed on asphalt surface 12 (Figures 1 and 2) while it is in a pliable state (i.e. after being freshly rolled with hot asphalt or after surface re-heating). Template 20 is then compressed into asphalt surface 12 with a drum roller 24 or some other compaction apparatus to form pattern 22 therein. For example, pattern 22 may be an impression simulating the appearance of bricks and mortar or some other decorative appearance. Template 20 is then removed from surface 12 to expose pattern 22 (Figure 1). In alternative embodiments, pattern 22 could consist of protrusions rather than impressions formed in surface 12, or some other surface texturing. Other similar means for forming pattern 22 in asphalt surface 12 may be envisaged.

15

[0032] One means for heating sheets 14 *in situ* is shown in Figure 3 and is described in WO 03/048458 A1 which is hereby incorporated by reference. In this embodiment, a portable surface heating apparatus 26 is provided for heating asphalt surface 12 and sheets 14 placed thereon. Preferably asphalt surface should be dry before the heating procedure commences. In the illustrated embodiment apparatus 26 includes a support frame 28 and a plurality of infrared heaters 30 supported for movement on support frame 28. For example, support frame 28 may include elongated rails 30 which are supported above asphalt surface 12 by support legs 32 and housing 34. A heater truck 36 is provided for reciprocating movement on rails 30. Truck 36 supports a bank of heaters 30 at positions close to surface 12 (e.g. approximately 2 inches above the ground).

[0033] As shown in Figures 4 and 5, after pre-formed thermoplastic sheet 14 is placed on asphalt surface 12 overlying pattern 22, infrared heaters 30 are reciprocated over sheet 14 to gradually melt the thermoplas-

30



tic material (in Figure 5, only the portion of apparatus 26 comprising heaters 30 is illustrated to aid in clarity). An important advantage of the heating method of Figure 1 is that a relatively large sheet 14, or group of sheets 14, and underlying asphalt surface 12 can be heated gradually and evenly. This approach avoids the disadvantages of hand-held torch heaters which cannot easily be used to evenly heat large areas and have a tendency to scorch the thermoplastic material and/or the underlying substrate. For example, depending upon their composition, some thermoplastic sheets 14 and/or asphalt surfaces 12 can scorch when subjected to sustained temperatures above approximately 325°F. In accordance with one embodiment of Applicant's heating method, asphalt surface 12 and thermoplastic sheet 14 are allowed to partially cool after each heating cycle. Thus the temperature of surface 12 (and sheet 14 applied thereto) increases gradually with successive heating cycles until the desired temperature suitable for thermoplastic/asphalt adhesion is achieved. The asphalt surface 12 is thereby subjected to a relatively slow heat soak to permit heat to gradually penetrate through and around sheet 14 below the uppermost surface layer of the asphalt. In accordance with one embodiment of the invention surface 12 and sheet 14 are gradually heated to a temperature within the range of 150 - 450°F and most preferably within the range of of approximately 150 - 450°F.

[0034] As shown in Figures 6 and 7, when sheet 14 is heated to a sufficiently high temperature it melts and conforms to pattern 22 formed in asphalt surface 12, forming a coating 10 thereon. The heat source is then removed and coating 10 is allowed to harden. In further embodiments of the invention colorants or additives may be applied to coating 10 while it is still tacky to create further surface texturing or augment the decorative effect. As shown in Figure 6, coating 10 may be applied to all or part of the surface pattern 22 depending upon the visual effect desired. If multiple sheets 14 are employed (Figures 8 and 9), sheets 14 may be aligned edge

to edge or gaps between adjacent sheets 14 may be maintained (i.e. portions of surface 12 imprinted with pattern 22 may remain uncoated).

[0035] Figures 10 - 12 show an alternative embodiment of the invention where pattern 22 is formed in both asphalt surface 12 and sheet(s) 14 simultaneously rather than sequentially. In this embodiment a pre-formed sheet 14 is placed on an unpatterned asphalt surface 12. Surface 12 may be in a freshly rolled, reheated or unheated state. As in the embodiment of Figure 5, infrared heaters 30 may reciprocated over sheet 14 to gradually melt the thermoplastic material (Figure 10). Once sheet 14 has been gradually heated to a sufficiently high temperature for adhesion to the underlying asphalt surface 12, a bond reduction agent is applied to the exposed surface 18 of sheet 14 (Figure 11). For example, the bond reduction agent may be a particulate bond breaker 40, such as sand, or a liquid spray 42, such as water coolant, applied to layer 18. The purpose of the bond reduction agent is to minimize adhesion between layer 14 and the pattern forming device.

[0036] As shown in Figure 12, the pattern forming device may comprise a removable template 20. In the illustrated embodiment, template 20 is used to simultaneously impress pattern 22 into both sheet 14 and underlying asphalt surface 12. The bond reduction agent referred to above minimizes adhesion between template 20 and the exposed surface 18 of sheet 14 while not affecting adhesion between surface 16 of sheet 14 and asphalt surface 12. The result is a patterned asphalt surface 12 having a thin thermoplastic coating 10 thereon (Figure 12).

[0037] As will be apparent to those skilled in the art in the light of the foregoing disclosure, many alterations and modifications are possible in the practice of this invention without departing from the spirit or scope

thereof. Accordingly, the scope of the invention is to be construed in accordance with the substance defined by the following claims.